

Stainless Steel Round Tubing for Mechanical & Structural Purposes

ASTM A554

Unit : mm

Outside Diameter	Thickness	Length
O.D. < 12.7 ± 0.10 (t ≤ 1.24) /	± 10%	3m < L ≤ 7.3m , +4.8 / -0
12.7 ≤ O.D. ≤ 25.4 ± 0.13 (t ≤ 1.65) / ± 0.25 (t > 1.65)		
25.4 < O.D. ≤ 38.1 ± 0.20 (t ≤ 1.65) / ± 0.25 (t > 1.65)		
38.1 < O.D. ≤ 50.8 ± 0.25 (t ≤ 1.24) / ± 0.28 (1.24 < t ≤ 2.11) / ± 0.30 (t > 2.11)		
50.8 < O.D. ≤ 63.5 ± 0.30 (t ≤ 1.65) / ± 0.33 (1.65 < t ≤ 2.77) / ± 0.36 (t > 2.77)		
63.5 < O.D. ≤ 88.9 ± 0.36 (t ≤ 4.19) / ± 0.51 (t > 4.19)		
88.9 < O.D. ≤ 127.0 ± 0.51 (t ≤ 4.19) / ± 0.64 (t > 4.19)		
127.0 < O.D. ≤ 190.5 ± 0.64 (t ≤ 6.35) / ± 0.76 (t > 6.35)		
190.5 < O.D. ≤ 406.4 ± 0.00125 x circumference		

Stainless Steel Square & Rectangular Tubes for Mechanical & Structural Purposes

ASTM A554

Unit : mm

Largest Outside Diameter	Thickness	Length
O.D. ≤ 31.8 ± 0.38	± 10%	3m < L ≤ 7.3m , +4.8 / -0
31.8 < O.D. ≤ 63.5 ± 0.51		
63.5 < O.D. ≤ 139.7 ± 0.76		
139.7 < O.D. ≤ 203.2 ± 1.52		